

ROKRACURE VP 5661

01.2010

Characteristic

Modified, aliphatic urethane acrylate

Application

Reactive, well wetting main binder for UV-curing systems with high flexibility and excellent (intercoat) adhesion on miscellaneous substrates, such as metal or plastic, due to low colour number also well-suited for wood applications

Form

70% DPGDA

Product specification

Functionality approx.

Resin	3
-------	---

Viscosity

dynamic viscosity

70% DPGDA / 25 °C	30000 - 50000	mPa·s
-------------------	---------------	-------

DIN 53214

Acid value

DIN ISO EN 2114	max. 2	mg KOH / g
-----------------	--------	------------

Colour

Gardner Color Standard

50% DPGDA	max. 3
-----------	--------

ASTM D 1544

Density

delivery form, 20 °C, approx.	1,1	g/cm ³
-------------------------------	-----	-------------------