

ROKRACURE VP 5762

01.2010

Characteristic

modified, aliphatic urethane acrylate

Application

High reactive, well wetting main binder for UV-curing systems with high hardness and excellent (intercoat) adhesion on miscellaneous substrates, such as metal or plastic

Form	70% DPGDA
-------------	-----------

Product specification

Functionality approx.

Resin	3,5
-------	-----

Viscosity

dynamic viscosity

70% DPGDA / 25 °C	10000 - 30000	mPa·s
-------------------	---------------	-------

DIN 53214

Acid value

DIN ISO EN 2114	max. 2	mg KOH / g
-----------------	--------	------------

Colour

Gardner Color Standard

50% DPGDA	max. 5
-----------	--------

ASTM D 1544

Density

delivery form, 20°C, approx.	1,1	g/cm ³
------------------------------	-----	-------------------